

## Teflon® FPX® coating on Anodized Aluminum Labels & Tags with Sub-Surface Photographic Image

CHARACTERISTIC	TEST CONDITION	EFFECT
Release Properties	Resists adhesion of various paints and coatings	N/A
Temperature Resistance	Servicable to 350°F (135°C)	N/A
<b>Chemical Resistance</b>		
Salt Spray	5% at 95 degrees F for 700 hr.	No corrosion
100% Hydrochloric Acid	1 hr. immersion	No effect
100% Hydrofluoric Acid	1 hr. immersion	No effect
80% Sodium Hydroxide	1 hr. immersion	No effect
Trichlorethylene	1 hr. immersion	No effect
Toluene	1 hr. immersion	No effect

Technical data is provided for comparison purposes only. This data has been compiled from sources we believe to be accurate but cannot guarantee. Variable combinations of chemicals, temperature, pressures and chemical concentrations may produce varied results. Customer testing is recommended to determine actual suitability in any specific environment.

☎ 800.382.2323 (toll free)  
☎ 858.549.9828

📞 858.549.8708  
✉ Mail@ExpressCorp.com

9155 Trade Place, San Diego, CA 92126 | ExpressCorp.com

ISO 9001:2008 Certified - ITAR Registered  
Member: Automatic Identification Manufacturers Association  
Member: AIM UID Supplier Alliance  
Member: National Assn. of Graphic Identification Product Manufacturers  
Member: Specialty Graphic Imaging Association

